66 FLEXLITE
PREMIUM WALL AND FLOOR LIGHTWEIGHT MORTAR

DESCRIPTION

Flexlite 66 is a premium-grade, non-sag lightweight mortar, for thin or medium-bed, wall, floor and ceiling installations. Unique, high polymer modification provides the superior bonding characteristics and exceptional flexibility required for installation of tile and stone over difficult to bond surfaces.
Flexlite 66 has Flexlite technology providing ease of installation and twice the coverage than traditional mortars as well as LEED point contribution due to over 20% recycled content.

INDUSTRY STANDARDS

Meets or Exceeds ANSI A118.4 and A118.11 specification requirements

BASIC USES

- Installation of porcelain, ceramic, mosaic, quarry and paver tile.
- Installation of natural stone, marble, granite, slate and precast terrazzo tile.

RECOMMENDED SURFACES

- Interior and most exterior floor, wall and ceiling installations*.
- Vertical or horizontal surfaces of concrete, masonry, terrazzo, cement backer boards.
- Installation over cement mortars and leveling compounds.
- Existing surfaces of properly prepared tile, stone or cementitious terrazzo.
- Exterior grade plywood or gypsum board, in interior dry areas only.
- Existing surfaces of properly prepared non-cushion sheet vinyl flooring, VCT or cutback adhesive residue.
- Flextile waterproofing, crack-isolation and sound reduction membranes.

**For commercial exterior wall and ceiling installations use Flextile 51 / 44 or Flextile 58XT systems.*

FEATURES

- Excellent for non-sag, thin or medium bed installations of large dimension, heavy textured tile and stone on both vertical and horizontal surfaces.
- Flexlite 66 formulated with Flexlite Technology promoting ease of troweling.
- 11.3 kg (25 lb) bag covers the same area as a 22.7 kg (50 lb) bag of traditional mortar.
- High flexibility and bond strength.
- Light color mortar: for light-colored natural stone, translucent marble and grout installations.
- For interior and most exterior floor, wall and ceiling installations.
- Formulated with recycled material, contributes to LEED certification.

LIMITATIONS

- Do not use over particleboard, Masonite, chipboard, OSB or similar unstable materials.
- Do not use over cushioned resilient flooring, rubber, plastic, paint, asphalt, or plywood surfaces in wet areas.
- Do not use directly over gypsum-based leveling compounds.
- Use only on surfaces, which are maintained at a temperature above 10°C (50°F) and below 35°C (95°F) during application and for at least 72 hours after application. Protect from freezing and complete water immersion for at least 7 days after installation. Seal partially used bags completely when not in use.
- Do not use over single layer plywood floors.
- Exterior wall applications limited to two-story installations, for higher facades use Flextile 51 with Flextile 44 additive. Consult Flextile's Technical Department. Use mechanical fasteners in installations of tiles larger than 720 sq. in (0.46 m^2) or weighing more than 15 lb (0.46 m^2) per sq. ft. (0.09 m^2). Check with local building codes with respect to height restrictions without mechanical fasteners.
- Do not use for installation of green marble and similar moisture sensitive tile. Use Flextile 58XT. Installations over nonporous surfaces may require extended setting/curing times.
- Do not use for complete water immersion installations such as swimming pools, steam rooms, spas. Use Flextlie 51 with Flextile 44 additive or Flextile 58XT.
- Do not use for moisture-sensitive stone such as green marble, certain limestone and granite, agglomerate tiles, cultured marble or resin-backed tiles.
- For installations subject to severe freeze/thaw conditions use Flextile two component systems.

TECHNICAL DATA at 23°C (73°F) and 50% humidity

Description	ANSI Spec.	Typical Result
7 Day Shear Strength	MPa (psi)	MPa (psi)
Glazed Wall Tile	>2.07 (300)	3.11 to 4.14 (450 to 600)
28 Day Shear Strength	MPa (psi)	MPa (psi)
Porcelain Mosaics Tile	> 1.38 (200)	2.59 to 3.45 (375 to 500)
Quarry Tile	> 1.03 (150)	2.76 to 4.14 (400 to 600)
Quarry Tile / Plywood	> 1.03 (150)	1.21 to 1.9 (175 to 275)

Typical Physical Properties

Pot Life	2 hours
Open Time	20 minutes
Initial Cure	24-48 hours
Final Cure	28 days
Cleanability	With water before material dries
VOCs	0 g/L
Shelf Life	1 year from production date when stored in dry, heated conditions

Certified VOC-Free
USGBC LEED v4, BD&C, ID&C

Approx. coverage per 11.3 kg (25 lb) bag:
5 mm (3/16") notched trowel - 10.0 m² (105 ft²)
6 mm (1/4") notched trowel - 7.1 m² (77 ft²)
10 mm (3/8") notched trowel - 5.5 m² (60 ft²)

** Coverages given are for estimating purposes only. Actual coverages may vary depending on job site conditions and installation techniques used.*

LEED Points Contribution

	LEED Points
MR Credit 4, Recycled Content	Up to 2 points
MR Credit 5, Regional Materials*	Up to 2 points
IEQ Credit 4.1, Low-Emitting Materials – Adhesives & Sealants	1 point
IEQ Credit 4.3, Low-Emitting Materials – Flooring Systems	1 point

**May be eligible*

INSTALLATION

PREPARATORY WORK

Surfaces must be sound, even, dry and free of grease, oil, dirt, paint, curing com- pounds or sealers, or other foreign matter. Surfaces must be true to a tolerance of ±3 mm (1/8") in 2.4 meters (8 ft.) for walls and 6 mm (1/4") in 3 meters (10 ft.) for floors. Concrete surfaces should have a wood float or steel trowel with broom finish, to a minimum CSP (Concrete Surface Profile) of 2 - 3. Roughen smooth concrete surfaces using mechanical abrasion such as grinding or shot/sand blasting or prime using Flextile 4050 FlexSil Primer. Plywood floors should be designed for maximum deflection of L/360 of span. This normally requires an over- lay of 16 mm (5/8") exterior grade plywood, or Flextile FlexMat Uncoupling Membrane over 25 mm (1") nominal boards or 16 mm (5/8") plywood when on joists 40 cm (16") O.C. Fasten overlay with screw type nails and glue where possible. Leave a 3 mm - 6 mm (1/8"-1/4") gap be- tween sheets of overlay and next to all vertical surfaces to allow for expansion. Refer to current editions of TTMAC 09 30 00 Tile Installation Manual, or TCNA Handbook For Ceramic Tile Installation for information regarding placement of movement or expansion joints, or for further substrate acceptability information. Per TTMAC and TCNA, floor systems, including the framing system and subfloor panels, over which the tile will be installed shall be in conformance with the Canadian National Building Code 2020, the International Residential Codes for residential applications, the International Building Codes for commercial applications, or applicable local building codes taking into consideration anticipated live and dead loads.

APPLICATION

Mix with approximately 5 – 5.1 liters (1.32 – 1.35 US gallons) of water per 11.3 kg (25 lb) bag. Avoid using high-speed mixers. Allow mixed mortar to slake for at least 10 minutes, then re-mix without adding further material or water. Spread a thin layer of mixed mortar with flat side of trowel to wet out the substrate; then reapply sufficient material with a suitably notched trowel that will leave enough mortar to give at least 85% (Interior applications) or 95% (Exterior and Large Format Tile applications) coverage to the backs of tile. It may be necessary to back-butter tiles in order to reach these requirements. (Refer to ANSI A108.5 specifications, and current TTMAC & TNCA guidelines regarding proper Flat Back-Troweling & Notch Back-Troweling methods for achieving proper bond coat transfer & coverage.) It is imperative that an appropriately sized trowel is used in conjunction with larger format tile or stone, so that adequate coverage is achieved.

Comb that area which can be covered with tile before skinning occurs. Mortar should be troweled with notches running in straight, parallel lines. Press or beat in tile while moving slightly in the opposite direction as shown of troweled mortar ridges, to achieve maximum coverage. Do not adjust tiles after they have been set for more than 20 minutes.

CURING AND GROUTING

Protect from all traffic and delay grouting until cured at least 24 hours, and preferably 48 hours. On exterior or cold weather applications, extended curing is recommended to ensure that mortar is sufficiently cured prior to grouting.
Grout using 1600 Ultra Performance Grout or Flextile Polymer Modified Grout or Flextile Flex-Epoxy 100-100% Solids Epoxy Grout.

CAUTION

Freshly mixed cement, mortar, concrete or grout may cause skin injury. Avoid extended contact with skin where possible and wash exposed skin areas promptly with water. If any cement or cement mixture gets into the eye, rinse immediately and repeatedly with water and get prompt medical attention.
Keep out of reach of children.

SAFETY

Refer to Flextile Safety Data Sheet for detailed health and safety information.

AVAILABILITY

Flexlite 66 Premium Wall and Floor Lightweight Mortar is available from Flextile Ltd. and its distributors in 11.3 kg (25 lb) bags.

WARRANTY

Flextile warrants that this product is of merchantable quality and is suitable for the purpose for which it is intended. Flextile's liability under this warranty shall be limited to replacement of its product found to be defective or, at its option, a refund of the purchase price.

MAINTENANCE

No maintenance is required except where damages result from unforeseen circumstances. Repair procedures shall be directed by Flextile or its distributors.

TECHNICAL SERVICES

Flextile maintains a well-equipped laboratory able to test its products in conjunction with the products with which they are used. Technical assistance for use of Flextile products is available upon request.

RELATED REFERENCES

Current editions of TTMAC 09 30 00 & TCNA Ceramic Tile Installation Manuals

TTMAC ACTTM

Notice: The information herein is the best information we have relating to our products and the recommended uses of our products are based on tests believed to be reliable. Flextile warrants each of its products is of merchantable quality and suitable for the purpose for which it is intended BUT DOES NOT MAKE ANY OTHER WARRANTY, EXPRESSED OR IMPLIED. This Warranty may not be enlarged or extended by our sales representatives, written sales information or drawings. Liability of Flextile under this warranty shall be limited to replacement of its product found to be defective or, at its option, a refund of the purchase price. All advice given and structural specifications supplied by Flextile representatives shall be used at the sole risk of those receiving the same and Flextile assumes no responsibility for the design or construction of any works in which its products are used. Any review or inspection of plans, buildings or product applications by Flextile representatives is not to be construed as approval thereof by Flextile. This information supersedes all previous issues and is subject to change without notice.