# ARDEX PANDOMO® ES/PS

**Clear Waterborne Epoxy Floor Primer** 

Clear Waterborne Two-Part Urethane Protective Wear Layer

# ARDEX PANDOMO® ES

Waterborne, two-part epoxy base coat primer. Use as a system with ARDEX PANDOMO® PS Urethane Protective Wear Layer to seal and protect.

# **Key Features**

- Designed for ARDEX PANDOMO® CF1, CF3, and K2
- Interior use

### Installation

- Packaging: 1 gallon (Part A: 0.80 gal; Part B: 0.20 gal) (Part A: 3 L Part B .75L)
- Coverage: 250 to 300 ft<sup>2</sup> (23 to 28 m<sup>2</sup>) per unit
- Installation:
  - 5 to 7 mils wet, which yields 2 to 3.5 mils dry (127 to 178 / 50 to 90 microns)
- Pot Life: 2 hours
- Dry Time: 2 to 4 hours to touch
- Apply ARDEX PANDOMO® PS: 4 to 6 hours

#### **Performance**

- Solids content: 43% (+/- 2%) by weight
  Adhesion: > 425 psi (concrete failure, no
- delamination)VOC: 145 g/L

# ARDEX PANDOMO® PS

A two-part urethane protective wear layer designed to be used as a top coat over ARDEX ES Epoxy Floor Primer.

# **Key Features**

- Designed for ARDEX PANDOMO® CF1, CF3, and K2
- Satin finish, non-darkening
- Stain resistant
- UV-stable
- Interior use only

#### Installation

- Packaging: One 5L (16.9 fl. oz.) bottle of Part A (Base)
   Two 500mL (16.9 fl. oz.) bottles of Part B (Cross Linker)
- Coverage: 1000 to 1050 ft<sup>2</sup> (93 to 97.5 m<sup>2</sup>) per kit
- Pot Life: 1 hour
- Time to Re-coat: 2 hoursLight Foot Traffic: 24 hours
- Full Cure: 7 days

## **Performance**

- **VOC:** < 110 g/L
- Gloss Level: Approx. 28







www.ardexamericas.com





