



EUROPEAN MAPLE GOTHA

European Maple Gotha is a 3-strip floor which is somewhat whiter than its American counterpart (Hard Maple) but has the same fine, light-brown grain.

PRODUCT DETAILS

Article Number	133N18EL50KW240
EAN Code	7393969034906
Surface Treatment	Silk matte finish
Dimensions	7 7/8 x 95 3/8 "
Weight per Package	54 lbs
Area per Package	36.6 sqft
Package info	Packages may contain start and stop boards.

DETAIL DESCRIPTION

Naturally occurring wood colour variations allowed, from light to dark. The product includes medium sound and black knots. Knots may vary in size and numbers.

COLOR CHANGE

Changes from cream white to golden cream.

FACTS

Wood Species	European Maple
Design	3-strip
Grading	Variation
Range	Kährs Avanti
Collection	Tres Collection
Resandable	2 times
Natural/Stained	Natural
Brinell Value	3,0
Joint	Woodloc® 5G
Floor heating	No
Warranty	20 years
Wear-layer material	Hardwood
Wear Layer Thickness	1/8"
Core material	Pine/Spruce lamella
Installation method	Floating, Glue-Down

TECHNICAL PROPERTIES

Moisture content	EN13183	7%±2%
Minimum Mean Density kg/m³	>500 kg/m³	
Reaction To Fire	EN13501-1	Dfl-s1
Formaldehyde Emission	EN717-1	E1
Content PCP	CEN/TR14823	≤ 5 x 10-6n
Breaking Strength N/mm²	EN1533	NPD
Thermal Conductivity	EN12664	0,14 W/mK
Thermal Resistance R-Value	.09 (m2K/W)	
Biological Durability	EN350-2	Class 1
CARB2	Compliant	
Slipperiness	CEN/TS15676	NPD

Other products in this collection



European Maple Gotha



Red Oak Nature



Ash Ceriale



Ash Vaila



Oak Bisbee



Oak Supai



Oak Pima



Oak Lecco

CERTIFICATES



Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.