

ALTEZZA CARRARA HD PORCELAIN TILE



ALTEZZA CARRARA HD PORCELAIN TILE



12" x 24" ALTEZZA CARRARA HD PORCELAIN TILE

ALTEZZA CARRARA HD PORCELAIN TILE



20" x 20" ALTEZZA CARRARA HD PORCELAIN TILE
68-320



13" x 13" ALTEZZA CARRARA HD PORCELAIN TILE
63-665



12" x 24" ALTEZZA CARRARA HD PORCELAIN TILE
69-993



2" x 2" ALTEZZA CARRARA HD PORCELAIN
MOSAICS 63-663



3" x 12" ALTEZZA CARRARA HD PORCELAIN
BULLNOSE 63-664

ALTEZZA CARRARA HD PORCELAIN TILE

PACKAGING INFORMATION

DESCRIPTION	ITEM CODE	LBS/BOX	PCS/BOX	SQFT/BOX	BOXES/SKID	SQFT/SKID
20"x 20" ALTEZZA CARRARA HD PORCELAIN TILE	68-320	59.71	6	16.15	26	421.62
13"x 13" ALTEZZA CARRARA HD PORCELAIN TILE	63-665	42.87	11	12.92	58	671.84
12"x 24" ALTEZZA CARRARA HD PORCELAIN TILE	69-993	58.12	8	15.50	32	496.00
2"x 2" ALTEZZA CARRARA HD PORCELAIN MOSAICS	63-663	38.45	10	9.69	48	465.12
3"x 12" ALTEZZA CARRARA HD PORCELAIN BULLNOSE	63-664	16.46	20	n/a	84	1680 pcs

GENERAL SPECIFICATIONS

DESCRIPTION	METHOD	UNIT	12" x 24"	13" x 13"	20" x 20"
THICKNESS		mm – in	8.5 mm – 11/32"	7.5 mm – 5/16"	8.7 mm – 11/32"
WATER ABSORPTION	EN ISO 10545-3	(%)	≤ 0.5	≤ 0.5	≤ 0.5
ABRASION RESISTANCE	EN ISO 10545-7	(PEI)	4	4	4
SCRATCH HARDNESS		(Mohs)	5	5	5
BREAKING STRENGTH	EN ISO 10545-4	(lbf)	≥ 400	≥ 300	≥ 400
CHEMICAL RESISTANCE	EN ISO 10545-13	(GL)	Class A – Res.	Class A – Res.	Class A – Res.
FROST RESISTANCE	EN ISO 10545-12		Resistant	Resistant	Resistant
STATIC COEFFICIENT OF FRICTION (WET)	ASTM C-1028	(μ)	≥ 0.60	≥ 0.60	≥ 0.60
STATIC COEFFICIENT OF FRICTION (DRY)	ASTM C-1028	(μ)	≥ 0.90	≥ 0.90	≥ 0.90
DCOF (WET)	ANSI B101.3		≥ 0.65	≥ 0.65	≥ 0.65
SHADE VARIATION			V2	V2	V2

* While the information has been presented with all due care, Anatolia Tile and Stone Inc. does not warrant the information is free from errors or omission. Actual colors may vary depending on product.