

LVMMax

General structure



General property

Physical Test	Unit	Value	Test Method
Total Thickness	μm	263±10%	ASTM D3652
Peel strength	gf/in	1400±100	ASTM D3652
Elongation(MD/TD)	%	180/140	ASTM D882A
Tensile Strength(MD/TD)	Kgf/mm ²	18/22	
Appearance	Naked eye	Transparency	Visual

NOTICE

- The technical data in this document are measured samples only and should not be used for any specification Purposes. - A term of validity is 6 months from the date of shipment and Keep it in a dry and cool place below 24°C without direct sunlight when stored.
- When applying Pressure Sensitive Adhesive film to any surface, be sure that the surface free from Oil or other surface contaminates such as powder, dust or release agent.
- Adhesive performance should be carefully checked when used on substrates containing plasticizers.

104TEL:82-102-10, 172BUN-3015-8307-GIL 8, SHINBONG 1 RO, SUJI Email : intlisco@naver.com- **GU, YONGIN-SI, GYEONGGIDO, KOREA**