



CGC FIBEROCK® BRAND TILE BACKERBOARD AND UNDERLAYMENT

DATA SHEET



DESCRIPTION

ENVIRONMENTALLY SUSTAINABLE, WATER-RESISTANT PANEL FOR INTERIOR TILE BACKER AND UNDERLAYMENT NEEDS

- Certified recycled content of 95%
- Uniform composition provides both strength and water resistance
- Use in both wet and dry areas throughout the home
- Ideal under tile, stone, vinyl, hardwood flooring, laminate flooring and carpeting
- Superior tile bond—three times industry standard
- Recognized by major resilient flooring and adhesive manufacturers
- Free of resins, adhesives and solvents that might stain a vinyl floor
- Provides a smooth, flat and paintable surface for wall applications
- Easy to cut, fasten and install
- CCMC Evaluation #12525-R

CGC Fiberock® Brand Tile Backerboard and Underlayment panels are manufactured from an environmentally sustainable, specially engineered combination of synthetic gypsum and cellulose fibers. CGC Fiberock Tile Backerboard and Underlayment panels have an integral water-resistant composition that offers durability, superior performance and exceptional tile bond. CGC Fiberock Tile Backerboard and Underlayment panels are engineered to meet water, mould and indentation resistance needs under and/or behind tile, resilient flooring, carpeting, hardwood flooring and laminate flooring in new construction and/or remodeling. CGC Fiberock Tile Backerboard is also an ideal substrate for painted wall surfaces, when transitioning from tile to paint.

CGC Fiberock Underlayment provides a smooth, flat surface that resists swelling and warping often seen with woodbased underlayments and contains none of the resins, adhesives or solvents that can stain floor covering materials. It also offers greater resistance to indentation than other underlayment products and can be used throughout a home in both wet and dry areas regardless of the flooring material chosen.

PRODUCT DATA

SIZES AND PACKAGING

DIMENSIONS¹	UNITS (PCS.)
6.4 mm (1/4") thick, 1220 mm (4') wide, 1220 mm (4') long	60
9.5 mm (3/8") thick, 1220 mm (4') wide, 1220 mm (4') long	60
9.5 mm (3/8") thick, 1220 mm (4') wide, 2440 mm (8') long	40
12.7 mm (1/2") thick, 915 mm (3') wide, 1525 mm (5') long	50

1. Other sizes are available. Contact your local CGC representative.

STANDARDS

CGC Fiberock Tile Backerboard and Underlayment panels meets ASTM standard C1278. Residential and light-commercial performance rating based on Robinson Floor Test (ASTM C627), conducted by The Tile Council of North America (TCNA).

AVAILABILITY

CGC Fiberock Tile Backerboard and Underlayment panels are distributed throughout Canada. Contact a CGC Inc. sales office or sales person for additional information.

COMPOSITION AND MATERIALS

CGC Fiberock Tile Backerboard and Underlayment panels are made from 95% recycled material and have earned independent certification from Scientific Certification Systems (SCS). SCS is the leading national testing company to evaluate manufacturers' environmental claims.

DELIVERY AND STORAGE OF MATERIALS

All materials should be delivered and stored in their original unopened package and stored in an enclosed shelter providing protection from damage and exposure to the elements. Store all CGC Fiberock Tile Backerboard and Underlayment panels flat.

ENVIRONMENTAL CONDITIONS

In cold weather and during CGC Fiberock Tile Backerboard and Underlayment panel and tile installation, temperatures within the building shall be maintained within the range of 5 to 38 °C (40 to 100 °F). Adequate ventilation shall be provided to carry off excess moisture.

APPLICATIONS

Wood framing shall approximate the moisture content it will reach in service by allowing the enclosed building to stand as long as possible prior to the application of the CGC Fiberock Tile Backerboard and Underlayment panels.



INSTALLATION

PANEL LAYOUT

- A. For flooring applications, lay cut edges against the wall; only factory edges should be joined. Begin laying panels at one corner. Maintain 6.4 mm (1/4") space between panels and perimeter walls. Stagger joints a minimum of 406 mm (16") so that four panel corners never meet and offset end and edge joints of panels a minimum of 305 mm (12") – 406 mm (16") from subfloor panel joints. Adjoin panel edges and ends lightly together. A maximum 0.8 mm (1/32") gap is allowed.
- B. For wall applications, install panels with ends and edges closely abutted, but not forced together. Stagger end joints in successive order.

TILE AND STONE APPLICATIONS

- A. For flooring applications over a wood-based substrate, laminate CGC Fiberock panels to subfloor using Type 1 organic adhesive or latex-modified thin-set mortar or dry-set mortar. Fasten to subfloor with 32 mm (1-1/4") CGC Durock™ Brand Tile Backer Screws for wood framing (or equivalent) or 38 mm (1-1/2") hot-dipped galvanized roofing nails spaced 203 mm (8") o.c. in both directions with perimeter fasteners at least 10 mm (3/8") and less than 16 mm (5/8") from ends and edges. Drive nails and screws so that bottoms of heads are flush with panel surface to ensure firm panel contact with subfloor. Do not overdrive fasteners.
- B. For wall application, fasten CGC Fiberock panels to framing with specified fasteners. Drive fasteners into field of panels first, working toward ends and edges. Hold panels in firm contact with framing while driving fasteners. Space fasteners a maximum 203 mm (8") o.c. for walls, 152 mm (6") o.c. for ceilings, with perimeter fasteners at least 10 mm (3/8") and less than 16 mm (5/8") from ends and edges. Drive nails and screws so that bottoms of heads are flush with panel surface to ensure firm panel contact with framing. Do not overdrive fasteners past panel surface. For steel stud applications (20 gauge or equivalent) use 32 mm (1-1/4") or 41 mm (1-5/8") CGC Durock™ Brand Screws for steel framing (or equivalent). For wood stud applications, use 32 mm (1-1/4"), 41 mm (1-5/8"), or 57 mm (2-1/4") CGC Durock Screws for wood framing (or equivalent) or 38 mm (1-1/2") hot-dipped galvanized roofing nails.
- C. For countertop applications, install minimum 19.1 mm (3/4") exterior grade plywood or OSB base across cabinet supports. Cover plywood base with CGC Durock™ Brand Tile Membrane, 15 lb. felt or 4 mil polyethylene and attach with 6.4 mm (1/4") galvanized staple. Fit ends and edges of CGC Fiberock panels closely but not forced together. Stagger panel joints from plywood base joints. Space fasteners 203 mm (8") o.c. around the perimeter and in the field of the board.
- D. Finishing panel joints: In areas that will be tiled, fill joints with latex-fortified mortar or Type 1 organic adhesive and immediately embed alkali-resistant, fiberglass mesh joint tape. In wall applications that will be painted: For taping use CGC Drywall Joint Tape with CGC Sheetrock® or Durabond® Brand Setting-Type Joint Compound. For finishing use CGC All Purpose Joint Compound. Do not use lightweight all purpose joint compounds on CGC Fiberock panels.
- E. Cut CGC Fiberock panels to size with a utility knife and straight edge. Use power saw only if it is equipped with a dust collection device and a NIOSH/MSHA approved respirator is worn. When using the score-and-snap method, score the panel twice and snap the panel away from the cut face. If a power-operated saw is used, a low-RPM portable saw with a 89 mm (3-1/2") carbide-tipped blade is recommended. When necessary to obtain neatly fitting joints, use a rasp or surform to smooth cut edges. Holes for pipes, fixtures and other small openings can be cut out with a saw or a drywall router equipped with a special bit.
- F. If waterproofing is desired, use CGC Durock Tile Membrane installed with CGC Durock™ Brand Tile Membrane Adhesive. See CGC literature piece DTM_DATA_CB492 for CGC Durock Tile Membrane product information.



RESILIENT FLOORING APPLICATIONS

- A. Fasten CGC Fiberock® Brand Underlayment to subfloor with minimum 6.4 mm (1/4") crown chisel point staples, hot dipped galvanized ring shank nails or corrosion resistant screws. Fastener length should be approximately equal to combined thickness of underlayment and subfloor. Fasteners should not penetrate through subfloor; long fasteners that penetrate the floor joists may compromise the ability of the subfloor to expand and contract uniformly with natural variations in temperature and humidity. Critical lighting situations should be considered when determining panel layout.
- B. Begin fastening where three panels intersect. Affix fasteners along joints in a zipper pattern at 25 mm (1") o.c., 6.4 mm (1/4") from panel edge. Install fasteners at 102 mm (4") o.c. in the field of panels. When using pneumatic tools, apply sufficient pressure on gun to prevent the tool from bouncing. Set pneumatic tool pressure to drive fasteners flush or slightly below underlayment surface. To prevent fastener heads from telegraphing through resilient floor covering, do not countersink more than 1.6 mm (1/16") below surface. Fasten one panel at a time. Begin at one end and fan out across the panel.
- C. Installing Panels Over Existing Vinyl Floor Covering – Do not install underlayment over cushion-backed vinyl. Ensure that existing floor is level, fully adhered and well bonded and meets appropriate design requirements. Repair missing or broken tiles, curling seams, severe gouges, protrusions of surface and any other damage with a high-quality floor leveler. Follow floor covering manufacturer's recommendations for installations over existing floors.
- D. Finishing Panel Joints – Use patching compound sparingly to fill wide joints, repair any surface voids and correct joint lippage (panel edge sitting above or below the floor plane). Carefully fill joints wider than 0.8 mm (1/32") and any surface imperfections with only enough material to infill void – do not feather. Correct joint lippage by applying patching compound to low side only and feathering to level. Allow compound to dry completely (90 minute minimum), then lightly sand or scrape, taking care not to scuff panel surface; use a flat blade to scrape away any excess material. Remove dust, dirt and debris from underlayment surface before application of floor covering.
- E. Applying Floor Covering – Refer to floor covering manufacturer's recommendations for proper procedures. For proper trowel selection, refer to adhesive manufacturer's recommendation for nonporous substrates. Follow floor covering and/or adhesive manufacturer's guidelines for setting times before allowing traffic on the finished floor. Follow floor covering manufacturer's recommendations for preventive maintenance, cautions and procedures.

LIMITATIONS

1. For interior use only. CGC Fiberock® Brand Tile Backerboard and Underlayment should not be used in exterior applications.
2. Do not use in areas subject to prolonged exposure to standing water; for instance, gang showers, saunas and hottub decks. If waterproofing is desired, use CGC Durock™ Brand Tile Membrane installed with CGC Durock™ Brand Tile Membrane Adhesive. See CGC literature piece DTM_DATA_CB492 for CGC Durock Tile Membrane product information.
3. Wall applications: Maximum stud spacing is 406 mm (16") o.c. Framing shall be designed (based on stud properties alone) not to exceed L/360 deflection for tile, L/240 for surfaces that will be painted. Maximum fastener spacing is 203 mm (8") o.c. for wood and steel framing; 152 mm (6") o.c. for ceiling applications.
4. Maximum dead load for ceiling system is 7.5 psf.
5. Do not use 6.4 mm (1/4") or 9.5 mm (3/8") CGC Fiberock panels for wall or ceiling applications.
6. Steel framing must be 20-gauge equivalent or heavier.
7. Do not use drywall screws or drywall nails.
8. Do not use drywall joint tape where tile or stone will be installed.
9. Floor tile applications: Maximum joist spacing is 610 mm (24") o.c. The subfloor system should be designed with a minimum deflection limit of L/360 for the span. Some finish materials may require a more rigid subassembly (such as large format tile and natural stone products). In these cases, follow the manufacturer's minimum requirements. The subfloor should be APA Span-Rated Plywood or OSB with an Exposure 1 classification or better with tongue and groove or back blocked at the unsupported edges.
10. Do not install directly over concrete subfloors.
11. CGC Fiberock panels are not designed for use as a structural panel.
12. CGC Fiberock panels must be finished, tiled or painted—not used as a finish surface.
13. Panels should not be exposed to sustained temperatures above 52 °C (125 °F).



TECHNICAL DATA

PROPERTY	UNIT OF MEASURE	ASTM TEST METHOD	12.7 mm (1/2") CGC FIBEROCK® BRAND TILE BACKERBOARD AND UNDER-LAYMENT	10 mm (3/8") CGC FIBEROCK TILE BACKERBOARD AND UNDER-LAYMENT	6.4 mm (1/4") CGC FIBEROCK TILE BACKERBOARD AND UNDER-LAYMENT
Flexural Strength	lbf	C473	> 110	> 70	> 40
Compressive Strength	MPa (psi)	n/a	> 3.4 (500)	> 6.9 (1000)	> 8.6 (1250)
Shear Bond Strength	psi	n/a	> 50	> 50	> 50
Water Absorption	% by wt. 24 hrs.	C473	> 5	> 10	> 10
Surface Nail-Pull Resistance	Grams	C473	1.6	1.6	1.6
Nail Pull Resistance	lb. (10 mm [3/8"] head diameter, wet or dry)	C473	> 120	> 90	> 70
Weight	Kg/m ² (psf)	C473	11.7 (2.4)	9.3 (1.9)	6.8 (1.4)
Mould Resistance	—	D3273	10 (no growth)	10 (no growth)	10 (no growth)
Surface Burning Characteristics	Flame/Smoke	E84 CAN/ULC S102	5/0	n/a	n/a
Thermal	"R"/k value	C518	0.39/1.27	—	—
Standard Method for Evaluating Ceramic Floor Tile Installation Systems	Passes cycles 1 – 6	C627	Light Commercial	Light Commercial	Light Commercial

PRODUCT INFORMATION

See cgcinc.com for the most up-to-date product information.

TRADEMARKS

The trademarks CGC, SHEETROCK, DURABOND, DUROCK, FIBEROCK, THE CGC LOGO, and related marks are trademarks of USG Corporation or its subsidiaries or its affiliates.

NOTE

Products described here may not be available in all geographic markets. Consult your CGC Inc. sales office or representative for information.

NOTICE

We shall not be liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods

not in accordance with current printed instructions or for other than the intended use. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from date it was or reasonably should have been discovered.

SAFETY FIRST!

Follow good safety/industrial hygiene practices during installation. Wear appropriate personal protective equipment. Read MSDS and literature before specification and installation.

Manufactured by:
CGC Inc.
350 Burnhamthorpe Rd. W, 5th Floor
Mississauga, ON L5B 3J1

