



Technical Information

- Flat Panel : 6"x24"
- Corner : 6"x18"x6"
- Thickness : 0.5"-0.75"
- Approx. Weight : 9.39 lbs.
- Type : Travertine
- Finish : Splitface
- Average Compressive Strength: Dry/7500 Psi



Color : Silver, Grey

Application : Walls, Barbeque areas, etc.

Adhesive

- **Exterior Application :** A flexible latex based mortar system suitable for the stone is recommended.
- **Interior Application :** A thin set mortar suitable for the stone is recommended.
- For light colored stones, a white mortar is recommended.

Packaging

- **Panels** : 6 pcs/box; 180 pcs/crate
- **Corners** : 4 pcs/box; 80 pcs/crate

Substrates

Exterior/Interior

- Fully cured concrete (at least 28 days cured)
- Masonry brick
- Regular brick
- Cement mortars
- Cementitious backer units

Interior only

- Gypsum plaster (max 10" high)
- Gypsum wallboard (max 10" high)
- Exterior grade plywood (max 10" high)
- Cementitious backer units

GENUINE STONE 