
























10 mm / COLOURED BODY PORCELAIN STONEWARE

E.N. 14411-ISO 13006 . Appendix G. Group B1a. GL	Test method	Reference value	Declared value	
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	Cl. 4 NOISETTE MATTE - GLOSSY
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	Cl. 3 CHOCO MATTE
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	Cl. 4 BLEU MATTE - GLOSSY
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	Cl. 2 CHOCO GLOSSY
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	Cl. 4 PERLE MATTE - GLOSSY
	Amount of water absorbed, in percentage	ISO-10545-3	E≤0,5%	average value 0,08%
	Glaze crazing resistance	ISO-10545-11	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	GB minimo / GB minimum / GB minimum / GB mindestens / GB minimo	GA
	Resistance to staining	ISO-10545-14	classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 mínimo	Cl. 4 GLOSSY
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Bending strength in N/mm2	ISO-10545-4	>35 N/mm2	average value 50 N/mm2
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET

	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,3\%$ ($\pm 1,5$ mm)	$\pm 0,2\%$
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,3\%$ (± 1 mm)	$\pm 0,15\%$
	Breaking strength in N (thickness $\geq 7,5$ mm)	ISO-10545-4	≥ 1300 Newton	average value 3200 N
	Thermal shock resistance	ISO-10545-9	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012)	DCOF	$> 0,42$ wet	$> 0,42$ wet MATTE
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLB GLOSSY
	Resistance to staining	ISO-10545-14	classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 mínimo	Cl. 5 MATTE
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,4\%$ ($\pm 1,8$ mm)	$\pm 0,35\%$
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,3\%$ ($\pm 0,8$ mm)	$\pm 0,1\%$
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLA MATTE
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	$\pm 5\%$ ($\pm 0,5$ mm)	$\pm 5\%$

Note:

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.