

Versabond Lite Professional Large and Heavy Tile Mortar

1 Product Name

Versabond Lite Professional Large and Heavy Tile Mortar

2 Manufacturer

Custom Building Products
 Technical Services
 10400 Pioneer Boulevard, Unit 3
 Santa Fe Springs, CA 90670
 Customer Support: 800-272-8786
 Technical Services: 800-282-8786
 Fax: 800- 200-7765
 Email: contactus@cbpmail.net
custombuildingproducts.com

3 Product Description

VersaBond® Lite offers all the performance of Versabond®-LFT with maximized creaminess and the benefits of a true lightweight mortar. This high bond strength formula is 30% lighter than a traditional mortar, resulting in a product that is easier to trowel and move around the jobsite. Designed for a wide variety of interior and exterior floor and wall installations, Versabond® Lite is excellent for setting large and heavy tile or stone. VersaBond® Lite will not sag on walls and offers nonslump performance for floor installations. Capable of LHT thin-set applications up to 3/4" (19 mm) thick on horizontal surfaces after beat-in. Formulated with CustomLite® Technology, a 35 lb. (15.9 kg) bag covers the same area as a 50 lb. (22.7 kg) bag of traditional mortar. Contributing to LEED® certification, VersaBondLite® contains up to 16.5% recycled content by weight and 2.5% recycled content by volume. Exceeds ANSI A118.4HET, and A118.11 performance without the need for additives. Meets ISO 13007 C2ETS1P1 performance.

Key Features

- High bond strength
- Non-slump - LHT thinset for us up to 3/4" thick
- Sag and slip resistant - immediately holds wall tiles in place
- Lightweight - 35 lbs. covers the same area as 50 lbs. of traditional mortar
- Exceptional creaminess for ease of troweling

Suitable Tile Types

- Vitreous, semi-vitreous or non-vitreous tile: ceramic, quarry, cement body tile, pavers
- Impervious porcelain and glass
- Brick and stone veneer
- Cement-based precast terrazzo
- Gauged or ungauged natural stone tile



Suitable Substrates

- Concrete, mortar beds, masonry, Portland cement plaster
- WonderBoard® Lite, cement and other industry-approved backerboards
- Liquid-applied and waterproofing membranes such as RedGuard® Waterproofing and Crack Prevention Membrane, Custom® 9240 and RedGuard® SpeedCoat
- Crack isolation sheet membranes such as Crack Buster® Pro
- Uncoupling mats such as RedGuard® Uncoupling Mat
- Substrates treated with MBP Multi-Surface Bonding Primer
- Exterior Grade Plywood (interior residential and light commercial dry areas)
- Gypsum wallboard (interior dry areas)
- Existing ceramic tile (sound stable, properly prepared/primed with MBP or Redgard in wet areas)
- Fully-bonded sheet vinyl flooring (sound stable, properly prepared/primed with MBP in dry areas)
- Plastic laminates (sound stable, properly prepared/primed with MBP in dry areas)
- Cutback adhesive (see preparation instructions)

Composition of Product

Modified dry-set mortar, which is a proprietary blend of Portland cement, inorganic aggregates, copolymers and chemicals.

Benefits of Product in the Installation

- High bond strength
- Suited for LHT thinset applications
- Non-sag, non-slump for heavy floor and wall tile and stone installation up to 3/4" (19 mm) thick
- Exceeds ANSI A118.4HET and A118.11 standards without the need for additives. Meets ISO 13007 C2ETS1P1 performance.
- 30% lighter than traditional mortars. A 35 lb (15.9 kg) bag covers the same area as a 50 lb (22.7 kg) bag of traditional mortar
- Not formulated with silica sand



Versabond Lite Professional Large and Heavy Tile Mortar

Limitations to the Product

- Do not bond directly to hardwood, Luan plywood, particle board, parquet, cushion or sponge-back vinyl flooring, metal, fiberglass, plastic or OSB panels.
- When setting moisture sensitive natural stone, cement or agglomerate tile use EBM-Lite™ Epoxy Bonding Mortar 100% Solids or CEG Lite™ 100% Solids Commercial Epoxy Grout.
- Do not use to install resin-backed stone use EBM-Lite™ Epoxy Bonding Mortar 100% Solids, CEG-Lite™ 100% Solids Commercial Epoxy Grout or contact Custom's® Technical Services for recommendations.
- For clear or translucent glass, CUSTOM recommends Glass Tile Premium Thin-Set Mortar. When setting glass tile larger than 6" x 6" (15 x 15 cm), contact Custom's® Technical Services for recommendations.
- When setting dimensional stone larger than 12" x 12" (30 x 30 cm), contact Custom's® Technical Services for recommendations regarding subfloor deflection requirements.

Packaging

- 35 lb (15.9 kg) bag
- Gray or white

4 Technical Data

Applicable Standards

American National Standards Institute (ANSI) ANSI A108.5, A118.4HET and A118.11 American National Standards for the Installation of Ceramic Tile. Meets ANSI A138.1 for Sustainable Tile Installation Products.

ASTM International (ASTM)

- ASTM C109 Standard Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)
- ASTM C627 Standard Test Method for Evaluating Ceramic Floor Tile Installation Systems Using the Robinson-Type Floor Tester

Resilient Floor Covering Institute (RFCI) Recommended Work Practices for Removal of Resilient Floor Coverings

Tile Council of North America (TCNA) TCNA Handbook for Ceramic Tile Installation, TCNA Method EJ171

International Organization for Standardization (ISO) 13007-2 for Thin Set Mortar.

Meets C2TES1P1 performance.

Technical Chart

| Property | Test Method | Requirement | Typical Results |
|----------------------------|-------------|----------------|--|
| Pot Life | | | 4 Hours |
| Open Time (E) | A118.4 | E = 30 Minutes | Pass |
| 4 Week Shear Bond Strength | | | |
| Glazed Wall Tile | A118.4 | > 300 psi | 450 - 550 psi (31.64 - 38.67 kg/cm ²) |
| Porcelain Tile | A118.4 | > 200 psi | 350 - 400 psi (24.61 - 28.12 kg/cm ²) |
| Quarry Tile to Plywood | A118.11 | > 150 psi | 150 - 200 psi (10.55 - 14.06 kg/cm ²) |
| Sag on Walls | A118.4 | < 0.02 mm | Pass |

Environmental Consideration

Custom® Building Products is committed to environmental responsibility in both products produced and in manufacturing practices. Use of this product can contribute towards LEED® certification:

- Up to 2 points towards MR Credit 5, Regional Materials
- Up to 2 points towards MR Credit 4, Recycled Content
- Up to 1 point towards IEQ Credit 4.1, Low-Emitting Materials – Adhesives & Sealants

Complies with CA Section 01350 and CDPH V1.2-2017.

See Additional LEED Information, including EPD/Environmental Product Declarations

at <https://www.custombuildingproducts.com/leed-information#LEED-Information/> .



5 Instructions

General Surface Prep

USE CHEMICAL-RESISTANT GLOVES, such as nitrile, when handling product.



Versabond Lite Professional Large and Heavy Tile Mortar

Surfaces must be structurally sound. Remove all grease, oil, dirt, curing compounds, sealers, adhesives or any other contaminant that would prevent a good bond. Glossy or painted surfaces must be sanded, or abraded, and stripped of all contaminants. Concrete must be cured 28 days and accept water penetration. Concrete must be free of efflorescence and not subject to hydrostatic pressure. Concrete slabs should have a coarse finish to enhance the bond. Plywood flooring including those under resilient flooring must be structurally sound and meet all ANSI and deflection requirements. For questions about proper subfloor installation, call Technical Services. Smooth concrete surfaces, existing glazed tile, terrazzo, or polished stone should be scarified. Sheet vinyl must be well bonded and stripped of old finish. Roughen the surface by sanding or abrading, then rinse and allow to dry. Expansion joints should never be bridged with setting material. Do not sand flooring materials containing asbestos.

Bonding to Concrete Surfaces

Concrete or plaster must be fully cured and must accept water penetration. Test by sprinkling water on various areas of the substrate. If water penetrates, then a good bond can be achieved; if water beads, surface contaminants are present, and loss of adhesion may occur. Contaminants should be mechanically removed before installation. Concrete must be free of efflorescence and not subject to hydrostatic pressure. Concrete slabs must be absorptive and not overly burnished. Mechanically abrade as needed.

Bonding to Lightweight Cement and Gypsum Surfaces

Lightweight or gypsum-based underlayments must obtain a minimum 2000 psi (13.8 MPa) compressive strength. The underlayment must be sufficiently dry and properly cured to the manufacturer's specifications for permanent, non-moisture permeable coverings. Surfaces to be tiled must be structurally sound and subject to deflection not to exceed current industry standards. Surfaces shall be free of all grease, oil, dirt, dust, curing compounds, waxes, sealers, efflorescence, or any other foreign matter.

All lightweight cement or gypsum surfaces should be primed with a properly applied sealer or a primer coat of RedGard, consisting of 1 part RedGard diluted with 4 parts clean, cool water. Mix in a clean bucket at low speed to obtain a lump free solution. The primer can be brushed, rolled or sprayed to achieve an even coat. Apply the primer coat to the floor at a rate of 300 ft²/gal (7.5 M²/L). Drying time depends on site conditions, but is normally less than 1 hour. Extremely porous surfaces may require 2 coats. At this point, RedGard can be applied to the primed lightweight or gypsum based surface. Refer to the individual product data sheet or packaging directions for application instructions. Expansion joints must be installed in accordance with local building codes and ANSI/TCNA guidelines. Refer to TCNA EJ171.

Bonding to Plywood Surfaces

Plywood floors, including those under resilient flooring, must be structurally sound and must meet all ANSI A108.01 Part 3.4 requirements. Maximum allowable deflection: L/360 tile L/720 stone. See TCNA F150-13 tile installations, TCNA F141-13 and F250-13 for stone. For questions about proper subfloor installation requirements, call Custom® Technical Services.

Bonding to Backerboards

WonderBoard Lite backerboard may be installed over structurally sound plywood subfloors for ceramic tile installations. Refer to TCNA F144-13 tile installations, TCNA F250-13 stone installations. Call Custom® Technical Services when installing natural stone over plywood subfloor.

Published Date: 3/22/2023

Bonding to Existing Surfacing Material

Resilient flooring, existing ceramic tile or plastic laminates must be well bonded, sound and stable, clean and free of all contaminants. Surfaces should be determined as suitable by owner or owners authority for the intended application. For interior dry areas use MBP – Multi-Surface Bonding Primer over dry existing surfaces as per the installation instructions. For wet area applications over existing ceramic surfaces, use RedGard® Waterproofing and Crack Prevention Membrane as per the installation instructions.

Bonding to Cutback Adhesive

Adhesive layers must be removed, as they reduce mortar bond strength to cement surfaces. Use extreme caution; adhesives may contain asbestos fibers. Do not sand or grind adhesive residue, as harmful dust may result. Never use adhesive removers or solvents, as they soften the adhesive and may cause it to penetrate into the concrete. Adhesive residue must be wet scraped to the finished surface of the concrete, leaving only the transparent staining from the glue. To determine desirable results, do a test bond area before starting. Refer to the RFCI Pamphlet, "Recommended Work Practices for Removal of Resilient Floor Coverings", for further information.

Movement Joint Placement

Movement joints are required for perimeters and other changes of plane in all installations. Expansion joints, perimeter joints and cold joints, as described in ANSI A108.01, should never be bridged with setting material. They must be brought through the tile work and filled with an appropriate elastomeric sealant, such as Custom's® 100% Silicone. Contact Custom's® Technical Services for the proper treatment of control or saw cut joints. Refer to TCNA EJ171, F125 and F125A.

See CUSTOM's Top Five Tips for Installing Movement Joints at <https://youtu.be/a6FL3LOhpt0>.

Mixing Ratios

Mix 6.25 - 6.75 qts (5.9 - 6.4 L) clean water per 35 lb (15.9 kg) bag of mortar.

Mixing Procedures

Mix by hand or use a low 150-200 RPM speed 1/2" (13 mm) drill to achieve a smooth, paste-like consistency. Let the mixture slake or stand 5-10 minutes; stir again and use. Stir occasionally, but do not add more water. When properly mixed, troweled ridges will stand without slump.



CUSTOM®

Versabond Lite Professional Large and Heavy Tile Mortar

Application of Product

Installation must conform to ANS A108.5 Using the flat side of a properly-sized notch trowel, apply with pressure, a thin coat of bonding mortar onto substrate surface and back of tile/stone as needed. With the notch side of the trowel held at a 45° angle, apply mortar to the surface, combing in one direction to the shortest side of the tile/stone body. Press tile firmly into place in a perpendicular motion across trowel ridges, moving in a back-and-forth motion. The perpendicular motion flattens ridges and closes valleys with mortar, allowing maximum coverage. With some tile/stone, back-buttering and/or back troweling is advisable. Using the flat side of a properly-sized notch trowel, apply with pressure, a thin coat of bonding mortar onto the back of the tile/stone using the notch side of the trowel (helpful for ungauged stone), comb mortar in same direction as substrate/surface mortar lines. Adjust tile/stone promptly and beat in/embed, with a beating block and rubber mallet as needed. Periodically pull up a tile/stone and check to ensure proper mortar/adhesive coverage. If the material has skinned over (not sticky to the touch), recomb with notch trowel; if too dry, remove and replace the dry mortar/adhesive with fresh material. Thin Set Mortar should not be used as a surface preparation material to fill low spots in walls/floors prior to installing tile, instead use an appropriate cement based patching material, https://www.custombuildingproducts.com/product_categories/patching. Mortar thickness should be less than maximum thickness of 3/4" after the tile/stone has been beat in/embedded. Ambient temperature should be maintained above 50° F (10° C) or below 100° F (38° C) for 72 hours to achieve proper bond.

See the "Trowel and Error" video for proper mortar application @ <https://youtu.be/Way5bMh-eYg>.

Curing of Product

Curing time is affected by ambient and surface temperatures and humidity. Use the following as a guideline. Allow 24 hours before grouting and light traffic. Allow 7-10 days before heavy or vehicular traffic. Before exposure to heavy or vehicular traffic, assure assembly is rated "Heavy or Extra Heavy" per TCNA Service Requirements. As necessary, use plywood or other load distributing protection when moving heavy equipment across tiled assembly. Submerged applications; wait 14 days after the final grouting period before filing water features with water at 70°F (21°C).

Cleaning of equipment

Clean with water before the material dries.

Storage

Protect from freezing. Store in a cool, dry area.

Health Precautions

DANGER: CAUSES SEVERE SKIN BURNS AND SERIOUS EYE DAMAGE. PROLONGED OR REPEATED INHALATION OF DUST MAY CAUSE LUNG DAMAGE OR CANCER. DO NOT BREATHE DUST OR SWALLOW. You cannot rely on pain to alert you to cement burns. Portland cement can cause dermatitis or sensitization. A NIOSH N95 respirator (mask) is recommended, especially in poorly ventilated areas, when use is frequent, or when permissible exposure limits may be exceeded. Immediately wash contaminated body and clothing thoroughly. If in eyes: rinse cautiously with water for several minutes; remove contact lenses if easy to do; continue rinsing. If inhaled: remove person to fresh air and keep comfortable for breathing. If swallowed: rinse mouth; do NOT induce vomiting. If you experience a burn, rash or skin irritation: immediately see a doctor. Immediately seek medical attention if any symptoms are significant or persist. In Emergency: 1-800-535-5053. **Contains silica sand and portland cement.** Before handling read Safety Data Sheet at www.custombuildingproducts.com.

KEEP OUT OF REACH OF CHILDREN.

WARNING: This product can expose you to chemicals including crystalline silica, which is known to the State of California to cause cancer, and hexavalent chromium compounds, which are known to the State of California to cause birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.

Conformance to Building Codes

Installation must comply with the requirements of all applicable local, state and federal code jurisdictions.

6 Availability & Cost

| Location | Item Code | Size | Color | Package |
|----------|-----------|-----------------|-------|---------|
| USA | VBLTMG35 | 35 lb (15.9 kg) | Gray | Bag |
| USA | VBLTMW35 | 35 lb (15.9 kg) | White | Bag |
| Canada | CVBLTMG35 | 35 lb (15.9 kg) | Gray | Bag |
| Canada | CVBLTMW35 | 35 lb (15.9 kg) | White | Bag |

7 Product Warranty

NOTICE: Obtain the applicable **LIMITED WARRANTY** at www.custombuildingproducts.com/product-warranty or send a written request to Custom Building Products, Inc., Five Concourse Parkway, Atlanta, GA 30328, USA. Manufactured by or under the authority of Custom Building Products, Inc. © 2021 Quikrete International, Inc.

8 Product Maintenance

Properly installed product requires no special maintenance.

9 Technical Services Information

For technical assistance, contact Custom technical services at 800-282-8786 or visit custombuildingproducts.com.

10 Filing System

Additional product information is available from the manufacturer upon request.



Versabond Lite Professional Large and Heavy Tile Mortar

Related Products

Polyblend®Plus Sanded Grout



Versabond Lite Professional Large and Heavy Tile Mortar

Coverage

SQUARE FOOT COVERAGE PER 35 LB BAG (SQUARE METER PER 15.9 KG)

| Trowel Size | Min Coverage | Max Coverage |
|---|----------------------------------|-----------------------------------|
| Longest side of tile less than 8" use 1/4" x 1/4" x 1/4" (6 x 6 x 6 mm) Square-Notch | 90 sq. ft. (8.4 M ²) | 100 sq. ft. (9.3 M ²) |
| Longest side of tile 8" to 15" use 1/4" x 3/8" x 1/4" (6 x 9.5 x 6 mm) Square-Notch | 63 sq. ft. (5.9 M ²) | 70 sq. ft. (6.5 M ²) |
| Longest side of tile more than 15"+ use 1/2" x 1/2" x 1/2" (13 x 13 x 13 mm) Square-Notch | 45 sq. ft. (4.2 M ²) | 50 sq. ft. (4.6 M ²) |
| Longest side of tile more than 15"+ use 3/4" x 9/16" x 3/8" (19 x 14 x 9.5 mm) U-Notch | 36 sq. ft. (3.3 M ²) | 40 sq. ft. (3.7 M ²) |

Recommended minimum coverage (80% for dry areas and 95% for wet areas and exteriors). Back buttering may be necessary.

Note that mortar coverage does not include backbuttering tiles. When backbuttering, consider the tile underside pattern and depth to estimate thickness and usage to add to your estimate.

Chart for estimating purposes. Coverage may vary based on installation practices and jobsite conditions. For more sizes, use the material calculator at CustomBuildingProducts.com or contact CUSTOM Technical Services at 800-282-8786.

Note that mortar coverage does not include flat back-troweling and/or notch back-troweling (formerly backbuttering) tiles. When back troweling, consider the tile underside pattern and depth to estimate thickness and usage to add to your estimate. The National Tile Contractors Association / Reference Manual has additional details regarding backbuttering, Flat & Notch Back-troweling at <https://www.tile-assn.com/page/refmanual>.



CUSTOM[®]