Richmond
indoor/outdoor carpet • tapis d'intérieur/d'extérieur

RICHMOND INDOOR/OUTDOOR – NEEDLEPUNCH CARPET INSTALLATION INSTRUCTIONS

- Ambient temperature must fall within the range of 65°F and 95°F.
- Use of a 3/32 x 3/32 x 3/32 V-notched trowel is recommended.
- Adhesive must be allowed time to tack.
- Properly tacked adhesive, when touched, will “leg” or string-up when your finger is pulled away from the adhesive.
- If the adhesive is allowed to dry past the proper tack, or the humidity levels are too high, this condition can cause all carpets to not adequately adhere to the adhesive; this will allow the installed product to move and/or wrinkle when trafficked.
- If needlepunch carpet is placed into an adhesive spread that has not come to a properly tacked state, seeing that the needlepunch products do not have a woven primary backing, the adhesive has the potential to bleed through to the face of the carpet.
- The use of a premium adhesive is recommended. Indoor/Outdoor adhesive is required for outdoor use.
- Rough surfaces should be repaired using an appropriate floor patch and/or leveler to achieve a smooth substrate.
- Unlike tufted outdoor carpets, needlepunch carpets should never be rolled with a weighted roller. Instead, they should be rolled using the carpet core or the flat edge of a push broom. By doing this, the installer can avoid adhesive bleed through to the carpet’s face.
- Although needlepunch is not a tufted carpet, it will still have a pile direction; it must be installed with the pile running in the same direction.
- Walking on needle punch carpet during and immediately after installation must be avoided, since this could cause a too wet adhesive to bleed through to the face of the carpet. Foot traffic should be avoided for a minimum of 24 hours.

August 2024

Richmond
indoor/outdoor carpet • tapis d'intérieur/d'extérieur

TAPIS INTÉRIEUR/EXTÉRIEUR RICHMOND – INSTRUCTIONS D'INSTALLATION DU TAPIS AIGUILLETÉ

- La température ambiante doit être maintenue entre 18°C (65°F) et 35°C (95°F).
- L'utilisation d'une truelle dentelée de 3/32 x 3/32 x 3/32 V est recommandée.
- Laisser le temps à l'adhésif de prendre pour qu'il colle bien.
- Lorsque l'on touche à un adhésif bien pris, il « s'étirera » et formera une traînée vers le haut lorsque l'on lève et éloigne son doigt de celui-ci.
- Si on laisse l'adhésif sécher au-delà du durcissement adéquat ou si les niveaux d'humidité sont trop élevés, cette condition peut faire en sorte que tous les tapis n'adhèrent pas adéquatement à l'adhésif, permettant ainsi au produit installé de bouger et/ou de se froisser en marchant dessus.
- Si le tapis aiguilleté est posé dans une application d'adhésif qui n'en est pas encore arrivé à un état d'adhérence adéquate, étant donné que les produits aiguilletés ne sont pas dotés d'une sous-couche primaire tissée, l'adhésif peut potentiellement transpirer au travers du tapis et se retrouver à la surface.
- L'utilisation d'un adhésif de qualité supérieure est recommandée. Un adhésif conçu autant pour l'intérieur que l'extérieur est nécessaire pour une utilisation du tapis à l'extérieur.
- Les surfaces inégales devraient être réparées en utilisant le produit de colmatage et/ou de nivelage de plancher qui s'impose afin d'obtenir un soubassement lisse.
- Contrairement aux tapis extérieurs tuftés, on ne doit jamais passer un rouleau lesté sur les tapis aiguilletés. On doit plutôt passer le cylindre à l'intérieur du rouleau de tapis ou l'extrémité plate d'un balai-brosse sur le tapis. En s'y prenant ainsi, l'installateur peut éviter que l'adhésif passe au travers du tapis et se retrouve à la surface.
- Même si tapis aiguilleté n'est pas un tapis tufté, son poil a quand même un sens et il doit être installé de façon à ce que le poil soit orienté dans la même direction.
- Marcher sur un tapis aiguilleté durant l'installation et immédiatement après doit être évité, puisque cela pourrait faire en sorte qu'un adhésif trop humide passe à travers le tapis et durcisse à la surface. On doit éviter de marcher sur le tapis pendant au moins 24 heures.

Août 2024