

TECHNICAL DETAILS CERTIFICATE

Reference	Acadia Grey Plus
Brand	Cecafi
Nominal Size	M 32cm x 57cm (12,7"x 22,5")
Wok Size	W 322mm x 573mm x 7,4mm (12,7" x 22,5"x 0,29")
Contains	11 pieces = 2,03m ² (21,53 Sqft)
Absorption Group	BIlb (6% to 10%)
PEI	4
Class Coefficient of Friction	Class I < 0,4

TECHNICAL CHARACTERISTICS	NORM	ISO 13006	UNIT	CARMELO FIOR SPECIFICATION
Deviation of average size from size (W)	10545-2	±0,60	%	±0,60
Deviation of average size from the average of 10 samples	10545-2	±0,50	%	±0,50
Thickness	10545-2	±5,0	%	±5,0
Straightness of sides	10545-2	±0,50	%	±0,50
Rectangularity	10545-2	±0,60	%	±0,60
Centre curvature, related to diagonal calculated from the wo	10545-2	±0,50	%	±0,50
Edge curvature, related to the corresponding work sizes	10545-2	±0,50	%	±0,50
Warpage related to diagonal calculated from the work sizes	10545-2	±0,50	%	±0,50
Surface quality	10545-2	≥95	%	≥95
Water absorption % by weight	10545-3	6 to 10	%	6 to 10
Modulus of rupture	10545-4	≥18	MPa	≥18
Breaking Strenght	10545-4	≥500	N	≥500
Thermal shock resistance	10545-9	To specify	-	Resistant
Moisture expansion	10545-10	To specify	mm/m	≤0,6
Grazing resistance	10545-11	Required	-	Resistant
Frost resistance	10545-12	To specify	-	Not resistant
Chemical resistance	10545-13	≥ Class GB	-	≥ Class GB
Resistance to acid and alkalis	10545-13	To specify	-	≥ Class GLB
Resistance to staining	10545-14	≥ Class 3	-	≥ Class 3
Resistance to water absorption stains	-	Specify	-	Product with higher strength - Class A


Darci F. Peruque Júnior
Gerente da Qualidade

Cerâmica Carmelo Fior Ltda
Estrada Municipal Carmelo Fior, Km 4 s/nº - CEP 13.490-970 / Cordeirópolis - SP / Brasil
55 (19) 3556-9600 / Fax 55 (19) 3556-9601
www.carmelofior.com.br