

AMBIENT

50cm
50cm




SPECIFICATIONS

Construction	LOOP
Product	Ambient
Pile Fiber Composition	100% Olefin
Yarn Type	BCF
Dye Method	Solution Dyed
Pile Weight	600 g/m ²
Number of Tufts	158000/m ²
Tufting Gauge	1/10"
Primary Backing	Non-Woven
Secondary Backing	StableShield-100% Vinyl
Optional Backings	Recova-PU Cushion, EcoShield, 100% Recycled Vinyl
Tile Size	50 cm x 50 cm
Pile Height	4.0 mm
Total Tile Height	6.0 mm
Pile Treatment	INVISTA Anti-Soil Treatment, Anti-Microbial (Optional)
Recommended Installation	Quarter Turn or Brick

Performance Specifications

VOC (Green Label Plus)	ASTM D5116-06	<0.5 mg/m ² /hour
Flammability (Pill Test)	ASTM D-2859//FF 1-70//16CFR 1630	Pass 8/8
Reaction to Fire	EN ISO 9239-1:2002	Dfl - s1
Static Propensity	ISO 6356	0.2 kV
Color Fastness	AATCC/16	5/5 on Grey Scale
Thermal Resistance	ISO 8302	.04m ² K/W
Impact Sound Insulation	ISO 140-8	ΔL _w 23dB
Sound Absorption Value	EN ISO 11654	α _w : 0.15(H)
Soiling Propensity	ASTM D 6540-00	4
Dimensional Stability	EN 986	< 0.20%
Castor Chair Test	DIN 54324	R ≥ 2.4

The above Information is subject to modification for the benefit of further improvement.



TORONTO - Email: toronto@centura.ca • **CALGARY** - Email: centura@telus.net • **HAMILTON** - Email: hamilton@centura.ca
EDMONTON - Email: centurae@telus.net • **LONDON** - Email: centura@centuralondon.com • **QUEBEC** - Email: quebec@centura.ca
OTTAWA - Email: ottawa@centura.ca • **WINDSOR** - Email: windsor@centuralondon.com • **MONTREAL** - Email: info.mtl@centura.ca
PETRBOROUGH - Email: centura@centura.ca • **VANCOUVER** - Email: vangeneral@centura.ca • **HALIFAX** - Email: halifax@centura.ca
MONCTON - Email: moncton@centura.ca • **ST. JOHN'S** - Email: stjohns@centura.ca

info@centura.ca | www.centura.ca

CENTURA

Available in roll of 78" for
bases and stairs