

SWEDEN

DRYBACK FLOORING

STYLE INFORMATION

Total Thickness (mm)	2mm
Underlayment	No
Wear Layer (mm)	0.3mm
CE Certification	YES
Utilization Class	
Coating	UV coating
Embossing	BP surface
Bevelled	Micro - Bevel
Click	No
Fiberglass	No

PACK INFORMATION

Plank Size	187x1227mm (7.36"x48.30")
Plank per box	12
Sqm per Box	3.6715m ² (39.52 sq ft)

CERTIFICATE



TECHNICAL INFORMATION

Density	1900kg/m ³	
Dimensional Stability	0.10%	ISO 23999/EN434
Abrasion Group	Class T	EN 660-2
Castor Chair Resistance	No Damage	EN 425
Squareness & Straightness	≤400mm : ≤0.25mm	ISO24342
	≥400mm : ≥0.35mm	
	≤0.01 in	ASTM F2055
Residual indentation	≤0.1mm	EN433
	≤8%	ASTM F1914
Impact Sound Insulation	6Bp	ISO 10140-3
Light Fastness	≥6	ISO 13893
Slip Resistance	R9	DIN51130
Chemical Resistance	ND (NOT DEFECTS)	ASTM F925
Thermal Resistance	ND	ISO 8302
Curling after exposure to heat	≤2mm	ISO 23999
Fire Resistance	Bfl-s1	EN13501
Flexibility	Passed	ISO 24344
	Passed	ASTM F137
Stain Resistance	Passed	ISO 26987
Underfloor heating suitability	Suitable	EN 12524
Formaldehyde group	E0	EN 717-1
Water Resistance	100%	
Burning cigarette test	No visible change	EN 1399:1997 Method B
Migration of Certain Elements	Not Detected	"EN71-3:1994 + A 1:2000 + AC: 2002 "
CPSIA section 108 - Phthalates	Not Detected	CPSC-CH- C1001-09.3